

Coating data chart



	Parylene	Electrostatic Epoxy	Liquid Epoxy
Layer thickness	~0.013 mm	0.1-0.3 mm	0.1-0.3 mm
UL number	UL94-V-0 E316885	UL94-V-0 E228348	UL94-V-0 E257126
Max. working temperature	90°C	200°C	200°C
Isolation voltage V _{DC}	>1000V (~12µm)* >2000V (~25µm)* (* layer thickness)	1000V 10 ≤ OD < 12 1500V 12 ≤ OD < 20 2000V OD ≥ 20	1000V 4 ≤ OD < 12 1500V 12 ≤ OD < 20 2000V OD ≥ 20
Roughness (comparative)	low	medium	medium
Advantages	-stress free -thin layer -clean -smooth and uniform	-good adherence -clean -high working temperature	-low stress -clean -good adherence -high working temperature -available for large toroids
Disadvantages	Only small toroids (OD < 10mm)	-not suitable for 3E15 -not for large toroids	-higher cost than electrostatic
Optimal application	Up to OD < 10mm	10 < OD < 51	-iron powder toroids -OD < 10 and OD ≥ 51 -suitable for 3E15
Coating generic type	paraxylene polymer	Electrostatic Epoxy-Polyamide	Epoxy-Polyamide
Melting point	175°C (few seconds)	---	---